

**Carleton Technologies Inc
Pressure Technology Division**

711 Corporate Center Court
Westminster, MD 21157
Telephone: 410-871-9966
Fax: 410-871-9960

Carleton, Pressure Technology Division, Technical Bulletin - 11/16/00**I. E-11005 Fiberglass “FRP” Cylinder Requirements***FRP Requirements*

Documentation required by DOT and retest procedure specified:	<ul style="list-style-type: none"> • Copy of exemption • CGA C-6.2 visual exemption • 49 CFR 173.34 (e) (15) for 3HT cylinders • Valid US-DOT retest identification number (RIN)
Retest period:	3 years
Maximum service life from month of manufacture:	15 years
Test pressure:	5/3 times service
Hold time at test pressure:	30 seconds
Cylinder permanent expansion rejection criteria – percent PE:	5% permanent expansion (limited number may be 10% - see exemption)
Cylinder elastic rejection criteria – percent REE:	None specified
If equipment failure, number of times cylinder may be retested:	Two times
Test date marking:	Label & epoxy coating

II. E-11005 Fiberglass “FRP” Cylinder Test Procedure

Carleton Technologies Inc, Pressure Technology Division, recommends the following process for the periodic hydrostatic retesting of composite cylinders manufactured with the manufacturer’s marks and under exemption numbers DOT-E-11005. Due to the nature of both the materials and design of the composite cylinders, it is not uncommon for the cylinder retest to be highly sensitive to the test water temperature and porous glass composite surface. These attributes can lead to a false, or higher than actual volumetric displacement.

This procedure is in accordance with US D.O.T. and T.C. regulations for the retest of cylinders. Please note if a cylinder fails during retesting; be certain to check your equipment, o-rings and sealing surfaces for leaks or damage.

- The retest cylinder and the test water must be the same temperature. To achieve this, fill the cylinder with water and allow it to set for no longer than four hours. This allows the fiberglass, aluminum and water to be at the same temperature. The water in the water jacket must be also be at the same temperature (+/- 3° Fahrenheit) of the water inside the cylinder. Filtered or deionized water should be used during the retesting. After retesting, make certain to clean/dry the interior of cylinder free of all water deposits.
- Immerse the cylinder in the water jacket and allow for it to soak for several minutes (at least 5 minutes, but no more than 60 minutes) before continuing the test.

- Pre-pressurize the cylinder to no more than 90% of its test pressure. The test pressure is $\frac{5}{3}$ times the service pressure that immediately follows the exemption number on the manufacturer's label. Hold this pressure for 90 seconds, or until stable, whichever is greater. Initially pressurize at no more than 200 psig per second, with the last psig at a rate of less than 50 psig per second.
- Return to 0 psig and carefully zero the burette.
- Pressurize to test pressure and hold for 60 seconds or until stable, whichever is greater. Carefully read and record the total expansion. Initially pressurize at no more than 200 psig per second, with the last psig at a rate of less than 50 psig per second.
- Return to 0 psig. Wait 90 seconds (until obvious movements of the water in the burette stabilize) prior to taking and recording the final expansion.